



Description

- One side metallized, one side treated, bi-oriented polypropylene film

Properties

- Two sides treated
- Enhanced metal adhesion

Typical Applications

- Specially designed to be used in triplex structures

Safeguards

- Release notes for Vibac Europe films are available on request

Typical values

PROPERTIES		UNITS	TEST METHODS		
Thickness		microns		18	35*
Grammage		g/m ²	DIN EN ISO 2286	16.38	31.85
Yield		m ² /Kg	1/2/3	61.05	31.40
TENSILE PROPERTIES					
Tensile strength	MD	N/mm ²	ASTM D882 DIN EN ISO 527-1/3	160	150
Elongation	MD	%		180	190
Secant Modulus 100%	MD	N/mm ²		110	100
Elastic Modulus 1%	MD	N/mm ²		2100	2100
Tensile strength	TD	N/mm ²		280	280
Elongation	TD	%		60	60
OPTICAL PROPERTIES					
Optical Density			IOQ 824.18	≥ 1.8	
THERMAL STABILITY					
Shrinkage (hot air 130° -5')	MD	%	OPMATC4a	4	
	TD			1	
COEFFICIENT OF FRICTION					
OPP layer / OPP layer			ASTM D1894	0.25	0.25
OPP layer / Met			DIN EN ISO 8295	0.20	0.20
METAL ADHESION		g/cm	IOQ 824.29	> 250	> 250
PERMEABILITY					
OTR	23°C 0% r.h.	cc/(m ² d atm)	ASTM D3985	120	120
WVTR	37.8°C 100% r.h.	g/(m ² d)	ASTM F1249	0.8	0.8
WVTR	23°C 85% r.h.	"	DIN 53122	0.17	0.17
TREATMENT					
Surface tension (OPP Layer)		dynes/cm	ASTM D2578	38	

(*)Thickness available upon request

Ed. 2 - 01.2006

Guidelines for storage of OPP film

No special conditions are required for the storage of OPP films but it is recommended that dry conditions below 30°C are employed to minimise any deterioration of surface discharge treatment level.

All OPP films should be allowed to reach operating room temperature for 24 hours before use.

Metallized (OPP) films are well known to age with time and it is recommended that stock should be evaluated for ink adhesion prior to printing and if necessary a primer employed. In case of deterioration of wetting tension level it is recommended that the material is re-treated prior to conversion to optimise adhesion of inks and adhesives.

Polypropylene films characteristics are maintained for 6 months from the date of production except for metallized layer surface tension.

Food contact

Vifan BTKZ complies with the requirements of EEC directives and FDA regulation. Specific documentation and migration test results are available upon request.

